

**Cusi Project - Recent drilling results from the Promontorio Sector:**

	From	To	Length	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)	True Width
DC07B154	111.6	112.2	0.6	0.1	413	0.1	0.4	0.7	0.3
Already reported	123.5	125.0	1.5	0.0	95	0.0	0.1	0.2	0.8
	138.5	140	1.5	0.00	108	0.00	0.10	0.10	0.8
	146	147.5	1.5	0.01	110	0.00	0.10	0.10	0.8
	324.5	325.5	1	0.02	92	0.10	0.60	0.50	0.6
	345.1	345.8	0.7	0.20	73	0.00	0.20	0.60	0.5
DC07B155	41.0	44.0	3.0	0.1	196	0.0	0.2	0.9	0.3
	48.5	50.0	1.5	0.1	146	0.0	0.1	0.3	0.1
DC07B157	53.0	62.0	9.0	0.0	148	0.0	0.1	0.1	3.8
DC07B158	No mineralisation								
DC07B159	No mineralisation								
DC07B160	4.5	5.5	1.0	0.0	126	0.0	0.3	0.2	0.2
	22.0	26.0	4.0	0.0	181	0.0	0.1	0.1	0.7
DC07B161	75.2	75.7	0.5	0.0	115	0.0	0.1	0.2	0.1
	123.0	127.5	4.5	0.1	182	0.0	0.2	0.2	0.8
	189.2	189.7	0.5	0.1	112	0.1	0.4	0.3	0.1
	300.2	301.2	1.0	0.1	115	0.0	0.1	0.2	0.2
	330.0	331.5	1.5	0.0	62	0.0	0.3	0.5	0.3
	393.0	394.8	1.8	0.3	680	0.1	2.2	3.3	1.2
DC07B164	No mineralisation								
DC08B166	65.0	66.5	1.5	0.0	322	0.0	0.0	0.1	1.1
	108.5	111.5	3.0	0.1	540	0.1	0.7	0.3	2.1
	126.5	128.0	1.5	0.2	516	0.1	0.2	0.1	1.1
	186.5	189.5	3.0	0.0	87	0.1	0.2	0.4	0.3
	222.0	223.0	1.0	0.1	113	0.0	0.2	0.1	0.7
	240.5	242.0	1.5	0.0	76	0.0	0.2	0.4	1.1
DC08B168	38.0	39.5	1.5	0.1	157	0.0	0.1	0.1	1.1
	42.5	45.5	3.0	0.1	234	0.0	0.1	0.1	2.1
	126.5	128.0	1.5	0.0	92	0.0	0.3	0.3	1.5
DC08B170	173.5	176.5	3.0	0.1	417	0.0	0.3	0.2	2.6
El Gallo Vein	182.5	187.0	4.5	0.3	443	0.0	0.4	0.4	3.9
DC08B171	In Process								
DC08B173	125.0	126.5	1.5	0.1	503	0.0	0.3	0.1	0.8
	197.0	198.5	1.5	0.1	83	0.0	0.2	0.7	0.8

**Recent drilling results from the Santa Edwiges – San Marina - SanSector**

	From	To	Length	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)	True Width
<b>Santa Edwiges</b>									
DC07B147	188.8	192.0	3.2	0.1	41	0.1	1.4	1.2	2.3
DC07B149	No mineralisation								
DC07B156	244.2	245.2	1.0	0.0	18	0.0	1.3	1.5	0.7
	269.5	270.5	1.0	0.1	112	0.0	0.1	0.3	0.9
	293.9	295.4	1.5	0.0	113	0.0	0.1	0.1	0.1
DC08B165	147.0	148.0	1.0	0.1	32	0.0	1.3	2.6	0.7
	158.0	164.0	6.0	0.6	16	0.0	2.1	1.2	4.2
	167.0	168.0	1.0	0.9	54	0.0	0.2	0.3	0.9
	172.0	173.0	1.0	1.0	82	0.0	0.1	0.1	0.1
	282.5	284.0	1.5	0.0	6	0.0	1.0	1.8	1.4
	287.0	293.0	6.0	0.3	54	0.1	3.7	4.0	5.6
	293.9	295.4	1.5	0.0	113	0.0	0.1	0.1	0.1
DC08B169	137.5	139.0	1.5	0.1	16	0.0	0.5	2.2	0.4
	243	246	3	0.06	22	0.00	1.00	1.40	2.1
	250	251.5	1.5	0.16	20	0.10	0.80	0.30	1.1
	305	306	1	0.16	57	0.00	2.30	2.20	0.3
<b>San Marina</b>									
<b>DC07B148</b>									
DC07B162	137.6	139.3	1.7	0.2	49	0.0	2.3	4.8	1.6
	145.0	145.5	0.5	2.3	86	0.0	4.4	1.6	0.5
	179.5	180.5	1.0	1.8	98	0.1	2.2	2.8	1.0
	247.2	250.5	3.4	0.1	10	0.0	1.5	2.1	0.9
	253.4	253.9	0.5	0.0	45	0.1	1.6	1.0	0.4
	256.0	257.4	1.4	0.2	51	0.2	3.9	4.4	1.0
	310.7	311.9	1.2	0.1	51	0.1	1.4	2.1	0.5
DC08B167	300.5	304.5	4.0	0.0	5	0.0	0.7	0.9	2.8
	340.0	341.2	1.2	0.1	35	0.2	3.1	3.1	0.8
	364.0	368.0	4.0	0.0	3	0.0	0.6	0.9	2.8
<b>San Marina</b>									
DC08B172	No mineralisation								